

TECHNICAL DATA SHEET

CLEAN-WRITE PAPER

<u>Product Code:</u> CRP0760-3, CRP0760-6, CRP0760-C, CRP0660-3W

Colors Available:

CRP0760-3 White, Blue, Yellow, and Pink CRP0660-3W(3 hole) White, Blue, Yellow, and Pink

CRP0760-6 White only

Sizes Available:

Three holed paper 8.5"x 11"

No hole paper 8.5"x 11", 11"x 17"

Continuous Feed 9.5"x 11"

Packaging:

8.5"x 11" 10 reams/cs 11"x 17" 5 reams/cs Continuous 1,500 sheets/cs

Specifications

Saturated cellulose documentation sheets enable you to control both contamination and information flow. Cellulose paper saturated with synthetic latex substantially reduces particle generation associated with standard papers. Unitek validates the quality of the materials with advanced testing and quality control to assure you of cleanliness and consistency. Manufactured with Cellulose base paper and synthetic latex.

Features

· Superior Writability

Cleanroom packaged

· Tear resistant and durability

Benefits

· Compatible with all laser, ink jet, and toner based printers

Made from the highest quality cleanroom compatible paper

Excellent Grip control even while wearing gloves

Smear Resistant



Typical Properties

| | TEST RESULTS Sub 22.5 |
|--|--------------------------|
| Basis Weight #/3000 ft² (Sub 22)** | 51.0 |
| Caliper (Mils) | 4.7 |
| Tear (g) MD CD | 105.0 95.0 |
| Tensile #/in MD | 36.0 |
| CD | 32.0 |
| Elongation % MD | 3.0 |
| CD | 8.0 |
| Mullen psi | 50.0 |
| Internal Bond (ozs/in) Porosity (seconds) | 13.0 5.0 |
| Extractible lons in Deionized Water (ppm) | |
| Chloride | 142.0 |
| Potassium Sodium | 60.3 284.0 |
| Nico Valetie Decides to (n/o2) | |
| Non-Volatile Residue In: (g/m²) De-lonized water | 0.31 |
| Isopropyl alcohol | 0.63 |
| Freon TF | 0.32 |
| Dry Particle Generation (≥ 0.5 microns) | |
| Helme Drum Test (ft³) (IES-RP-CC-003-87T) | 24,772 |

^{*}These data are typical properties and are not intended to serve as specifications